

Coloured Floor Oil based on vegetable oils and waxes

Characteristics

Hard-wearing, resistant to wine, beer, cola, coffee, tea, fruit juices, milk and water according to DIN 68861 1A. Resistant to saliva and sweat according to DIN 53160. Meets all the demands of children's toys according to EN 71. Floorservice Color Hardwax-Oil Classic deepens the natural structure and leaves a coloured haze on the treated surface.

Applications

All kind of parquet and wooden floors, as sealer or final treatment. Contains: castor oil, natural resin-ester, isoparaffin, safflower oil, kaolin, bentonite, microwax, silicic acids, zinc carbonate, cobalt, zirconium, zinc and manganese octoate as drying components, colour pigments.

Technical data

Working temperature: not below 16°C.

Hardening time: 10 days.

Drying time: 8-12 hours, depending on temperature and ventilation. After a drying time of 3 days the floor can be used with caution.

Usage: 1 litre = about 12 - 15 m² in two layers or 24 - 30 m² in one layer.

Storage tools: with Floorservice Parquet Cleaner.

Storage: cool and dry. In case of an already opened packaging skin forming could appear. The skin has to be removed before using the product.

Warning: put clothes drenched with Color Hardwax-oil in water (danger of spontaneous combustion!). Afterwards they can be disposed off with normal garbage.

Cleaning: Floorservice Parquet Cleaner.

Maintenance: Floorservice Maintenance oil.

EU-limit for this product (cat. A/e): 400 g/l (2010). This product contains max. 390 g/l VOC.

Colours: 24 different shades available.

Packing: 250 ml, 1 litre

Instructions for use

Stir well.

Color Hardwax-Oil is ready to use. The surface must be well sanded (up to grain 120), dry (humidity of the wood max. 14%) and free of dust and grease. Apply the Color Hardwax-Oil thinly and evenly using the special floorbrush, a mop or a spatula. Within 10 to max. 15 minutes rub the oil in with a buffing machine using a thick white pad and remove excess oil with a felt pad. After a drying time of 8 - 12 hours (depending on temperature and ventilation) apply a second layer accordingly. In case of a very absorbent surface a third layer is recommended.

In case of exotic wood (for example Iroko, Kambala, Jatoba and Afzelia) apply only one layer, otherwise you could provoke drying problems. After three weeks time, a layer of Floorservice Maintenance oil (natural or Color) can be applied.

Above product information and recommendations are given in good faith and based on practical tests following long term research and development. We cannot assume responsibility for any work as the ultimate results depend on factors beyond our direct control. In cases of doubt always test the product in advance.

01.10.2009

